

TRACTOL

TRACTOL aerosols are always ready-to-use.

You don't need thinners, cleaner, paintbrush or stirrer to achieve a perfect finish.



- The outside temperature must not be too cold, 20°C is ideal.
- Shake the can vigorously for about 2 minutes making sure the mixer ball can be clearly heard in the can. This is very important to ensure that the coloured pigments is well stirred and mixed in. **This is the only way to obtain the right paint colour.**
- If possible spray outdoors, or in a well-ventilated room (cellar, workshop or garage). Indoors you must cover the surrounding area well to protect it from the fine misting of spray paint. Mask any areas not to be painted. Good illumination is also important, to let you see whether you have painted over the whole area.

Spraying:

- Never spray straight away onto the object to be painted. Spray first onto a test piece e.g. a newspaper or masking material.
- Be sure to spray from the correct distance of 25 - 30 cm.
- Different objects call for different spray techniques. Start spraying close to the object but not directly onto it. Press the actuator button down fully. Move the can slowly and evenly back and forth, changing direction only after the spray has moved past the object. This makes it easier to control the amount of paint falling onto the object and lets you ensure that too much paint does not build up, forming runs or "tear drops".
- Don't try to get a perfectly smooth surface at the first pass. The first pass should be regarded as a preparatory coat on which you will build a smooth even finish with the second and perhaps third passes, spraying before the previous coat is fully dry, but with 1 or 2 minutes between each pass. Further coats can then only be applied after 24 hours, otherwise there is the risk of lifting.

Drying Time (at +20°C, 50% relative air humidity):

The drying time depends on surrounding temperature, air humidity and thickness of the applied coat

- Dust-dry: after approx. 10 minutes
- Dry to touch: after approx. 30 minutes
- Over workable: after approx. 2 - 4 hours

Black

DESCRIPTION	400ml Aerosol
MF Gloss Black	AERO26
MF Dull Black	AERO40

Grey

DESCRIPTION	400ml Aerosol
MF Stoneleigh Grey	AERO15
MF Silvermist Grey	AERO20
Ford Tractor Grey	AERO48

Yellow

DESCRIPTION	400ml Aerosol
JCB Yellow	AERO18
John Deere Yellow	AERO61

Blue

DESCRIPTION	400ml Aerosol
Ford Tractor Blue	AERO16
NH Ford Blue	AERO419

Red

DESCRIPTION	400ml Aerosol
MF Red	AERO1

Primer

DESCRIPTION	400ml Aerosol
Grey Primer	AERO604

Green

DESCRIPTION	400ml Aerosol
John Deere Green	AERO5

White

DESCRIPTION	400ml Aerosol
Gloss White	AERO45